

## 技术参数表 Technology Data Sheet

名称Name	PG75水胶-60g格底	75mic synthetic film Acrylic-60gsm white glassine		
面材Face wood	PG75合成纸	75mic synthetic film		
胶水Glue	水性型压敏胶	Acrylic		
底材Underwood	60g白格拉辛硅纸	60gsm white glassine		
技术指标 Technical index	参数值 Argument value	单位 Unit	方法 Method	产品说明 Description of products
<b>面材Face Wood</b>				<b>材料特性Material Behavior</b>
克重 Gram weight	55±2	g/m2	GB/T 451.2-2002	材料由聚丙烯发泡薄膜在表面涂有混合碳酸钙涂层组成，具有良好的表面性能，并且防水耐撕裂，适用于平张印刷、胶版印刷、柔版印刷、碳带打印等多类别印刷工艺。
厚度 Thickness	72±2	um	GB/T 451.3-2003	The material is composed of polypropylene foam film coated with mixed calcium carbonate coating on the surface. It has good surface properties, waterproof and tear resistant. It is suitable for multiple printing processes such as flat sheet printing, offset printing, flexographic printing and carbon strip printing.
涂层 Coated	Yes	Yes/No	试剂擦拭 Reagent wiping	
<b>胶粘剂Adhesive</b>				<b>材料特性Material Behavior</b>
环形初粘 Looptack on SS	>900	gf/Inch	FTM-9	材料为丙烯酸水性压敏胶，是环保型材料，具有良好粘性及耐候性，可应用于多种材质的粘贴，材料不耐水并且不可接触其他化学试剂。
剥离强度 90°Peel on SS	>500	gf/Inch	FTM-2	The material is acrylic water-based pressure-sensitive adhesive, which is an environmentally friendly material with good viscosity and weather resistance. It can be used for pasting various materials. The material is not water-resistant and can not contact other chemical reagents.
持粘力 Shear	>12	Hr	FTM-8	
<b>底材 Liner</b>				<b>材料特性Material Behavior</b>
成品克重 Gram weight	58±3	g/m2	GB/T 451.2-2002	材料为高紧致度超压纸张表面带有离型涂层，具有良好平整性、抗拉强度及透明，适合应用于不干胶产品卷筒印刷、模切及后道自动贴标等应用。
厚度 Thickness	50±3	um	GB/T 451.3-2003	The material is high compactness overpressure paper with release coating on the surface, with good flatness, tensile strength and transparency, suitable for roll printing, die-cutting and automatic labeling of self-adhesive products.
<b>产品储存及使用环境Product storage and use environment</b>				<b>产品应用Product application</b>
储存环境：在温度25±10℃、相对湿度50±20%的情况下，有效期为6个月。超过有效期的产品，经检验合格仍可使用。 Storage environment: In the case of temperature 25±10℃, relative humidity 50±20%, valid for 6 months. Products beyond the expiration date can still be used after passing the inspection. 贴标环境：10℃<贴标温度<50℃，湿度50%±20%RH。 Label environment: 10℃< Label temperature <50℃, humidity 50%±20%RH. 应用环境：-20℃<应用温度<60℃。 Application environment: -20℃ < Application temperature < 60℃.				广泛应用于日化、食品饮用、医疗、工业标签等包装材料解决方案。 Widely used in daily chemical, food and drinking, medical, industrial labels and other packaging material solutions.
<b>特别说明Special note</b>				
1.盈之泰所有有关材料的说明、技术信息及使用推荐是基于我们认为可信的测试结果，但不构成一种担保。 2.由于产品的使用条件和加工条件不同，在使用之前请测试，避免未知的风险。 3.技术文件以盈之泰现行条款为准，盈之泰公司保留最终解释权。 1. All descriptions of materials, technical information and recommendations for use by Yingzhitai are based on test results that we believe to be credible, but do not constitute a warranty. 2. Due to the different use conditions and processing conditions of the product, please test before use to avoid unknown risks. 3. The technical documents shall be subject to the current terms of Yingzhitai, and Yingzhitai reserves the right of final interpretation.				