

GB/T451

FTM-7

**FTM-10** 

**FTM-10** 

**FTM-10** 

## **Technical Data Sheet**

Product name: Product code:	70gsm white PEK	release paper	(10-15gf)	Report date Versions	2024/6/3 FT/QA01
Material property					
Project		Unit	Parameter values	Executive	standard
Ration		g/m <sup>2</sup>	70±3	ISO	536
Thickness		um	80±3	ISO	534
Wide in width	1	mm	-	Tape m	easure

 $g/m^2$ 

 $g/m^2$ 

gf

gf

gf

%

>75 FTM-11 The material is high-quality pulp and paper surface coated with a release coating, which has good flatness and tightness, and is suitable for applications such as flat printing and cutting of selfadhesive products

12±2

 $1.2\pm0.2$ 

6-8

8-12

10-15

## Service environment

PE grammage

Coating grammage

Quick Release force

NT Release force

Aging release force

Residual continuation rate

Material characteristics

Project		<b>Environment description</b>		
	Storage environment:	Temperature 25±10°C	Humidity 50±10%	
	Application environment:	Temperature 25±10°C	Humidity 0~85%	

## Attention

1. All descriptions, techniques and recommendations for the use of the materials by Fortey are based on test results that we believe to be credible, but do not constitute a guarantee.

2. Due to the different conditions of use and processing of the product, please test before use to avoid unknown risks. 3. The technical documents shall be subject to the current terms of Fortey, and Fortey reserves the right of final interpretation.

address: Changhongling Industrial Park, Nanhai District, Foshan City, Guangdong Province Tax: 0757-85225867 Tel: 0757-85225298