

Technical Data Sheet

Product name:	80g gsm yellow PEK release paper (10-15gf)	Report date	2024/6/3
Product code:		Versions	FT/QA01

Material property

Project	Unit	Parameter values	Executive standard
Ration	g/m ²	78±3	ISO536
Thickness	um	94±3	ISO534
Wide in width	mm	-	Tape measure
PE grammage	g/m ²	10±2	GB/T451
Coating grammage	g/m ²	1.2±0.2	FTM-7
Quick Release force	gf	6-8	FTM-10
NT Release force	gf	8-12	FTM-10
Aging release force	gf	10-15	FTM-10
Residual continuation rate	%	>90	FTM-11
Material characteristics	The material is high-quality pulp and paper surface coated with a release coating, which has good flatness and tightness, and is suitable for applications such as flat printing and cutting of self-adhesive products		

Service environment

Project	Environment description	
Storage environment:	Temperature 25±10°C	Humidity 50±10%
Application environment:	Temperature 25±10°C	Humidity 0~85%

Attention

1. All descriptions, techniques and recommendations for the use of the materials by Fortey are based on test results that we believe to be credible, but do not constitute a guarantee.
2. Due to the different conditions of use and processing of the product, please test before use to avoid unknown risks.
3. The technical documents shall be subject to the current terms of Fortey, and Fortey reserves the right of final interpretation.

address: Changhongling Industrial Park, Nanhai District, Foshan City, Guangdong Province

Tax: 0757-85225867

Tel: 0757-85225298